



Test Report # **VOYAGER-0001-102615**

TOWNSEND LEATHER NFPA 260 COVER FABRIC BURN REPORT

Date: **10/26/2015**

Conditioning Chamber: Time In: 11:10 AM
10/23/2015

Time Out: 2:05pm
10/26/2015

THICKNESS: 1.0 - 1.2 MM

Specimen: **Townsend Leather**

Voyager Cowhide

Standard Filling Material: Non FR polyurethane foam, density 20 kg/m³ to 25 kg/m³
Test

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	No	12.7
2	No	15.2
3	No	12.7

CLASS I ☒

CLASS II ☐

Tested according to NFPA 260 : 2013 Edition-Section 6.1 Cover Fabric Test

Dawn Finch

Quality Control

Townsend Leather Co. Inc.

45-49 Townsend Ave PO Box 669

PO Box 669

Johnstown, NY 12095

This form is electronically signed. If you need an actual signature, please call.